1600 W. Blancke St. Linden, NJ 07036 Tel: (908) 474-9393 Fax: (908) 474-9388

Technicure® RX-3

Fast-Cure Amine Curing Agent For Epoxies

Typical Properties

Appearance: Clear Liquid

Amine Value: 340

Viscosity @20C: 1000 cps
Mix Ratio BADGE EEW 190: 50 PHR
Gel Time, 100g Mass@20C: 7 min

Advantages

- Fast Cure
- High Clarity
- Excellent Adhesion to a variety of substrates
- Excellent Thermal Shock Stability
- Cures as low as 5 deg C 40F

Uses

Technicure® RX3 is a modified cycloaliphatic diamine, room temperature curing agent designed for colorless, fast cure epoxy systems that cure as low as 40 degrees F. RX3 shows clarity and good thin film cure. It's low vapor pressure, and low viscosity and easy mix ratio make RX3 excellent for repair compounds, flooring and coatings.

A&C Catalysts, Inc. is not responsible for the use of the information, and no warranty is made of the merchantability or fitness of any product. Purchasers of any product must determine whether the product is acceptable for their particular purpose, under their own operating conditions. Moreover, nothing herein waves any of A&C Catalysts, Inc. conditions of sale. Nothing herein shall imply the nonexistence of any relevant patents or to constitute permission, inducement or recommendation to practice any invention covered by any patent, without authority from its owner.