



## A&C Catalysts, Inc.

1600 W. Blancke Street  
Linden, NJ 07036  
908-474-9393  
908-474-9388 fax

A & C Catalysts Product Selector			
Product Name	Description	Particle Size	Packaging
<b>Ajicure® Curing Agents</b>			
Ajicure PN-23( J)	Epoxy imidazole adduct curing agent/acc for DICY; long out time	10 micron and 2 micron (J)	10 kg box
Ajicure MY-24	Epoxy amine adduct curing agent/ stable acc for anhydrides or DIC	10 micron	10 kg box
Ajicure AH-300	Modified version of PN-23, contains 20% DICY	10 micron	20 kg box
Ajicure MY-25	Very stable version of MY-24. Stable to 100°C, cures at 115°C	10 micron	10 kg box
Ajicure PN-40 (J)	More stable version of PN-23. Stable to 90°C, cures at 110°C	10 micron and 2 micron (J)	10 kg box
Ajicure PN-50 (J)	More stable version of PN-40. Stable to 100°C, cures at 115°C	10 micron and 2 micron (J)	10 kg box
<b>Technicure® Curing Agents</b>			
Technicure ADH-J	Adipic dihyrazide, water soluble will cure epoxy acrylic and urethane	3 micron	25 kg drum
Technicure IDH-J	Isophthalic dihyrazide High Tg crosslinker	3 micron	25 kg drum
Technicure D-44	DICY (44 micron or 325 mesh)	44 micron or 325 mesh	40 lb box, 960 lb/skid
Technicure D-10	DICY (10micron or 1250 mesh)	10 micron or 1250 mesh	40 lb box, 960 lb/skid
Technicure D-5	DICY (5 micron or 1400 mesh)	5 micron or 1400 mesh	25 lb box, 600 lb/skid
Technicure Nano-Dicy	Ultrafine DICY, 1-2 micron average	>90% less than 5 micron	25 lb box, 600lb skid
<b>Technicure® Accelerators</b>			
Technicure LC-80 (J)	Encapsulated imidazole curing agent accelerator for epoxies	10 micron or 2 micron (J)	40 lb box, 960 lb/skid
Technicure LC-100 (J)	Encapsulated tertiary amine for epoxy and anhydride cures	10 micron or 2 micron (J)	40 lb box, 960 lb/skid
Technicure MDU-11M	MDI urea accelerator	6 micron, 44 max	25 lb box, 600 lb/skid
Technicure PDU-250M	Phenyl dimethyl urea	6 micron, 44 max	40 lb box, 960 lb/skid
Technicure TDU-20M	Urea accelerator based on TDI	6 micron, 44 max	40 lb box, 960 lb/skid
Technicure DCMU	Dichloromethyl urea technical grade	6 micron, 44 max	40 lb box, 960 lb/skid
<b>Resicure® Imidazoles</b>			
Resicure 2-PHICN	1-(Cyanoethyl)2-phenyl-4,5-dicyanoethoxymethyl imidazole	Viscous liquid	18 kg pail, 1 Kg Jar
Resicure EMI-24-CN	1-(2-Cyanoethyl)2-ethyl-4-methyl imidazole	200 cps liquid	18 kg pail, 1 Kg Jar
Resicure EMI-24 (EMI-24LV)	2-Ethyl, 4 methyl imidazole	Liquid	18 kg pail, 200 kg Drum
<b>Technirez®</b>			
Technirez DGA	Aniline diglycidyl ether, difunctional tertiary amine epoxide	Low viscosity liquid (~120cps)	5 gal pail, 55 gal drum
Technirez RME-30	35% CTBN modified "3" type solid epoxy	Pellets or 80 mesh	50 lb bag
Technirez RME-912	33% CTBN modified "4" type solid epoxy	Pellets or 80 mesh	50 lb bag
Technirez NC-36	36% CTBN modified liquid novolac epoxy	Semi-solid	40 lb Pail
Technirez NP20/B2	20% Carboxylated rubber modified epoxy	80 mesh	40 lb pail
Technirez NP15/N5	20% Carboxylated rubber modified solid novolac epoxy	80 mesh	40 lb pail
Technirez FR-001	Phosphonate ester liquid flame retardant, 21% phosphorous	Liquid	5 gal pail, 55 gal drum